ZIRCONIUM AND HAFNIUM

(Data in metric tons, unless noted)

<u>Domestic Production and Use</u>: Zircon sand was produced at two mines in Florida. Zirconium and hafnium metal were produced from zircon sand by two domestic producers, one in Oregon and another in Utah. Both metals are present in the ore typically in a Zr to Hf ratio of 50:1. Primary zirconium chemicals were produced by the Oregon metal producer and at a plant in New Jersey. Secondary zirconium chemicals were produced by about 10 other companies as well. Zirconia (ZrO₂) was produced from zircon sand at plants in Alabama, New Hampshire, New York, and Ohio, and the metal producer in Oregon.

Zircon refractories and foundry applications are the largest end uses for zirconium. Other end uses of zirconium include abrasives, chemicals, metal alloys, welding rod coatings, and sandblasting. The largest market for hafnium metal is as an addition in superalloys.

Salient Statistics—United States:	<u> 1991</u>	<u> 1992</u>	<u>1993</u>	<u>1994</u>	<u>1995</u> °
Production: Zircon (ZrO ₂ content) ¹	67,000	70,300	W	W	W
Imports:					
Zirconium, ores and concentrates (ZrO ₂ content)	23,200	24,300	45,500	53,300	68,200
Zirconium, alloys, waste and scrap (ZrO ₂ content)	702	745	798	837	840
Zirconium oxide (ZrO ₂ content)	NA	NA	1,950	2,400	3,700
Hafnium, unwrought, waste and scrap	3	2	3	5	5
Exports:					
Zirconium ores and concentrates (ZrO ₂ content)	20,400	18,100	23,400	20,800	23,600
Zirconium alloys, waste and scrap (ZrO ₂ content)	1,870	2,310	2,020	1,640	2,150
Consumption, zirconium ores and concentrates,					
apparent, (ZrO ₂ content) ²	72,700	78,000	W	W	W
Prices:					
Zircon, dollars per ton:					
Domestic	340	215	NA	NA	NA
Imported, f.o.b. U.S. east coast	340	255	200	278	330
Zirconium sponge, dollars per pound	9-12	9-12	9-12	9-12	9-12
Hafnium sponge, dollars per kilogram	165-210	165-210	165-210	165-210	165-210
Net import reliance as a percent of					
apparent consumption ²					
Zirconium	1	8	12	W	W
Hafnium	NA	NA	NA	NA	NA

Recycling: Zirconium metal was recycled by four companies, one each in California, Michigan, New York, and Texas. The majority of the zirconium recycled came from scrap generated during metal production and fabrication. Zircon foundry mold cores and spent or rejected zirconia refractories are often recycled. Recycling of hafnium metal was insignificant.

Import Sources (1991-94): Zirconium ores and concentrates: Australia, 56%; South Africa, 43%; and other, 1%. Zirconium, wrought, unwrought, waste and scrap: France, 55%; Germany, 13%; Japan, 12%; Canada, 11%; and other, 9%. Hafnium, unwrought, waste and scrap: France, 96%; Germany, 3%; and other, 1%.

<u>Tariff</u> : Item	Number	Most favored nation (MFN) 12/31/95	Non-MFN ³ 12/31/95	
Zirconium ores and concentrates	2615.10.0000	Free	Free.	
Germanium oxides and ZrO ₂	2825.60.0000	3.7 ad val.	25% ad val.	
Ferrozirconium	7202.99.1000	4.1% ad val.	25% ad val.	
Zirconium, waste and scrap	8109.10.3000	Free	Free.	
Zirconium, other unwrought, powders	8109.10.6000	4.2% ad val.	25% ad val.	
Zirconium, other wrought, alloys	8109.90.0000	5.5% ad val.	45% ad val.	
Unwrought hafnium, waste and scrap	8112.91.2000	Free	25.0% ad val.	

Depletion Allowance: 22% (Domestic), 14% (Foreign).

<u>Government Stockpile</u>: In addition to 14,500 tons of baddeleyite ore held in the National Defense Stockpile, the U.S. Department of Energy (DOE) held over 500 tons of zirconium in various forms. DOE also maintained a supply of approximately 35 tons of hafnium.

ZIRCONIUM AND HAFNIUM

		Stockpile Status—9-30-95			
Material	Uncommitted inventory	Committed inventory	Authorized for disposal	Disposals JanSept. 95	
Baddeleyite	14,500		<u> </u>	_'	

Events, Trends, and Issues: Demand for zirconium ores and concentrates outpaced supply, causing prices to increase sharply. Increased demand was driven by consumption in the ceramics industry where zircon is used in ceramic tiles and glazes. Shortages of material were expected in the coming years.

Availability of hafnium continued to exceed supply. Surpluses were stockpiled in the form of hafnium oxide. The demand for nuclear-grade zirconium metal, the production of which necessitates hafnium's removal, produces more hafnium than can be consumed by the metal's uses.

Zirconium and hafnium exhibit nearly identical properties and are not separated for most applications. However, zirconium and hafnium are separated for certain nuclear applications. Because hafnium is a strong absorber of thermal neutrons, zirconium-clad fuel rods in nuclear reactors are hafnium-free to improve reactor efficiency. At the same time, hafnium is used in reactor control rods to regulate the fission process through neutron absorption.

<u>World Mine Production, Reserves, and Reserve Base</u>: World primary hafnium production statistics are not available. Hafnium occurs with zirconium in the minerals zircon and baddeleyite.

	Zirconium				. Hafnium	
	Mine production ^e (thousand metric tons)		Reserves ⁴ Reserve base ⁴ (million metric tons, ZrO ₂)		Reserves ⁴ Reserve base ⁴ (thousand metric tons, HfO ₂)	
	<u>1994</u>	<u> 1995</u>				
United States	W	W	1.7	5.3	32	97
Australia	502	500	6.3	27.0	114	484
Brazil	20	20	.4	.4	7	7
Chinae	15	15	.5	1.0	NA	NA
India	18	20	3.4	3.8	42	46
South Africa	245	260	14.3	14.3	259	259
Ukraine ^e	65	65	4.0	6.0	NA	NA
Other countries	<u>21</u>	_20	<u>.9</u>	<u>4.1</u>	<u>NA</u>	<u>NA</u>
World total (may	be					
rounded)	⁵890	⁵900	32	62	450	890

<u>World Resources</u>: Resources of zircon in the United States included about 14 million tons associated with titanium resources in heavy-mineral sand deposits. Phosphate and sand and gravel deposits have the potential to yield substantial amounts of zircon as a future byproduct. Eudialyte and gittinsite are zirconium silicate minerals that have a potential for zirconia production. Identified world resources of zircon exceed 60 million tons.

Resources of hafnium in the United States are estimated to be about 130,000 tons, available in the 13-million-ton domestic resources of zircon. World resources of hafnium are associated with those of zircon and baddeleyite and exceed 1 million tons.

<u>Substitutes</u>: Chromite and olivine can be used instead of zircon for some foundry applications. Dolomite and spinel refractories can also substitute for zircon in certain high-temperature applications. Columbium (niobium), stainless steel, and tantalum provide limited substitution in nuclear applications, while titanium and synthetic materials may substitute in some chemical plant uses.

Silver-cadmium-indium control rods are used in lieu of hafnium at numerous nuclear power plants. Zirconium can be used interchangeably with hafnium in certain superalloys; in others, only hafnium produces the desired or required grain boundary refinement.

^eEstimated. NA Not available. W Withheld to avoid disclosing company proprietary data.

¹ZrO₂ content of zircon is typically 65%.

²Defined as imports - exports + adjustments for Government and industry stock changes.

³See Appendix B.

⁴See Appendix C for definitions.

⁵Excludes the United States.