JCP H30 Imitation Parchment, Laser-finish, White, Natural White, and Colored Parchment Paper Archival Quality

Use Information: This paragraph is informational only and is not exclusively definitive of the end use. For high quality offset printing of announcements, certificates, citations, diplomas, enrolled bills, etc. requiring processing in copiers and laser printers; execution with pen and ink, erasing quality, and highest degree of permanence (archival quality) when specified. Printed matter may include text and line illustrations; suitable for embossing

Stock: 100% bleached chemical woodpulp.

<u>Note</u>: Not less than 30% postconsumer fiber. Any percent over 30 percentage points, is encouraged, provided that the requirements of this Standard are met.

Basis weight: 17 by 22 inches, 500 sheets (pounds)	24	32	47
Folding endurance: Average not less than (MIT double folds)	28	30	30

Ruling and writing quality: Lines ruled and character written with ball point and felt tip pens shall be clear cut and free from excessive feathering.

Erasing quality: Paper shall retain good ruling, writing, and typing quality, texture, and surface appearance, without ink spreading after repeated erasure.

Watermark: Paper shall not be watermarked.

Curl: Paper shall like flat before and after processing through a high speed copier or laser printer with either no tendency to curl or with a curl which can be overcome under reasonable working conditions.

February 1, 2008

FSC 9310

General appearance: Paper shall conform to the standard sample(s) established by the Government.

<u>Brightness</u>: The white paper shall have a target brightness not less than 79% or as specified.

<u>Color</u>: The paper in the order (or publication) shall be uniform and the color variation shall not exceed DE(CIELAB) = 1.0.

For colored stock, paper shall match one of the established color standards in Part 3 or match a color sample supplied by the ordering agency. Colors shall not fade or transfer (rub off) and shall appear even and uniform on the surface of the sheet. The sheet shall not be 2-sided.

Finish and formation: Shall be uniform.

<u>Cleanliness</u>: The dirt count for each side of the paper shall not exceed 250 specks per square meter. No sample sheet $(600 \text{ to } 650 \text{ cm}^2 \text{ in size})$ shall contain more than one defect with equivalent area of 0.25 mm^2 or greater.

OPTION 1

Archival paper. This option is for products requiring permanence (archival quality). Add the following properties.

Acidity: pH value by cold extraction shall be not less than 7.5. The paper shall contain not less than 2% calcium carbonate.

<u>Note</u>: Any deviation in this requirement is sufficient cause for rejection of the paper.

Tearing strength: Average, each direction, not less than (grams) 50 70 100

ANSI/NISO: Conformance to the standard Z39.48—1992 allows the printing of the infinity symbol (oo) in the document or publication.

Testing: Shall be conducted in accordance with methods in part 2, *Government Paper Specification Standards*. The acceptance criteria Part 4 does not apply.

¹ This grade is typically not available in less than mill run quantities.