**Use Information**: This paragraph is informational only and is not exclusively definitive of the end use. For face and back offset printing of top covers for tablets, separators, wrapping for packages, etc. Printed matter may include text and line illustrations.

| <b>Stock</b> : 100% unbleached sulphate pulp. <u>Note</u> : Not less than 5% postconsumer fiber. Any percent over 5 percentage points, is encouraged, provided that the requirements of this Standard are met. |    |    |    |    |    | <b>Bursting strength:</b> Average not less than (lb/in <sup>2</sup> ) | 28 | 34 | 38  | 42  | 47  |  |
|--|----|----|----|----|----|---|----|----|-----|-----|-----|--|
| <b>Basis weight</b> : 24 by 36 – 500 sheets (pounds)   | 40 | 50 | 60 | 70 | 80 | Tearing strength: Average each direction not less than (grams)        | 70 | 90 | 110 | 130 | 150 |  |
|  |    |    |    |    |    | General appearance: Paper shall conform to the standard               |    |    |     |     |     |  |

sample(s) established by the Government.

**Testing**: Shall be conducted in accordance with methods in part 2, *Government Paper Specification Standards*. The acceptance criteria Part 4 shall apply.