FAILURE CRITERION OF GLASS FABRIC REINFORCED PLASTIC LAMINATES

Osamu Haga, Noriyuki Hayashi and Kazuo Kasuya

Translation of "Glass cloth sekiso kyoka plastic no hakai kijun", Japan Society of Materials Science, Journal, Vol. 25, No. 273, June 1976, pp. 516-520

(NASA-TM-88406) FAILURE CRITERION OF GLASS N86-23657 FABRIC REINFORCED PLASTIC LAMINATES (National Aeronautics and Space Administration) 11 p HC A02/MF A01 CSCL 11D Unclas G3/24 06003



NATIONAL AERONAUTICS AND SPACE ADMINISTRATION WASHINGTON D.C. 20546 APRIL 1986

by Osamu Haga, Noriyuki Hayashi *** and Kazuo Kasuya ***

Tension, compression and combined tension-compression biaxial tests were performed on three types of glass fabric reinforced plastic laminates, and the applicability of an interaction formula was investigated. Based on these results a new combined tension-compression biaxial failure criterion have been derived. The results obtained are as follows;

(1) The interaction formula can be used practically as the uniaxial failure criterion of glass fabric laminates when it is transformed into the equation containing tensile or compressive strength in the direction having an angle of 45 degree to one of the anisotropic axes.

(2) In the case of closely woven plain fabrics, the interaction formula can be applied as the combined tension-compression biaxial failure criterion, but in the case of coarsely-woven plain fabrics, the calculated values do not agree well with the experimental results.

(3) The values calculated according to the new combined tension-compression biaxial failure criterion agree fairly with the experimental results. When this criterion is applied to the case of uniaxial loading, the formula becomes the same as that of the uniaxial failure criterion given in (1). (Received Sep. 22, 1975)

1. Introduction

In general, there are unidirectional fiber reinforced plastics in which fiber is arranged in one direction, laminated in which the unidirectional fibers are laminated perpendicularly or obliquely and laminates which are laminated with fabrics, such as glass cloth, containing a plastic matrix in continuous fiber reinforced plastics. Many theoretical and experimental studies concerning yield and failure of the former material by combined stress have been accomplished (Reference (1) to (4)) but there are few studies directly concerning glass cloth laminate of the latter.

The strength characteristics of glass cloth laminates are different from those of unidirectional reinforced plastic or its laminates; it seems to be from the influence of the wave condition of woven fabrics, woven conditions and twined condition of fiber. The authors are studying biaxial stress-failure criterion of laminated reinforced plastics made of glass fiber and in this report, the results of experimental studies concerning failure criterion under tension-compression biaxial stress conditions are reported.

* Received Sept. 22, 1975

** Official member, The engineering dept. of Chiba University, Yayoi-cho, Chiba
*** The engineering dept. of Chiba University, Yayoi-cho, Chiba
**** Numbers in margin indicate foreign pagination.

1

/16

ORIGINAL PAGE IS OF POOR QUALITY

2. Failure Criterion

2.1. Failure criterion of uniaxial tension and uniaxial compression There is a report which tried to make tension failure criterion of glass cloth laminate reinforced plastic from the characteristics of the content materials (Reference (5)) but it seems to be difficult to generalize for glass cloth laminates with differently woven cloth because the report does not consider the influence of the weave. However, it would be very difficult to consider the influence of weave on strength. Thus the authors adopted a criterion which is a little modified from the Interaction formula (Reference (6)) proposed by Norris by considering the strength of composite material including the influence of weave as the base. For the coordinate system shown in Fig.1, the stress $\mathcal{T}(\theta)$ in the X direction with angle \mathfrak{E} against the anisotropic axis L can be written as equation (1) by applying the coordinate conversion rule to the interaction formula.

 $|\sigma^{-\theta}| = \frac{F_L F_T S_{TT}}{(F_T^2 S_{TT}^2 + a_0 F_L^2 S_{TT}^2 + b_0 F_L^2 S_{TT}^2 + b_0 F_L^2 F_T^2 F_T^2}$ (1)

According to equation (1), when \mathcal{E} is close to 45°, the stress does not match the actual measured value thus an equation which uses the tensile strength or compressive strength F_{45} ° at \mathcal{E} =45° instead of the shear strength S_{LT} is conducted, i.e., \mathcal{E} = 45° is applied to the equation (1) and solve S_{LT} then apply it to equation $\frac{17}{17}$ (1) again.

$$(\theta) = \frac{1}{\sqrt{(l^2 - m^2)\left(\frac{l^2}{F_L^2} - \frac{m^2}{F_T^2}\right) + \left(\frac{2lm}{F_{45}}\right)^2}}$$
(2)

In the case that two materials which have the same strength are laid up in different ply orientation, equation (2) can be simplified as shown below by applying $F_L=F_r=F$.

$$\sigma(\theta) = \frac{1}{\sqrt{\left(\frac{1}{F}\cos 2\theta\right)^2 + \left(\frac{1}{F_{45}}\sin 2\theta\right)^2}}$$
(2)

From equation (2) or (2)', if tensile or compressive strength in the direction of the anisotropic axis and the direction of 45° from the axis is given, the failure strength of the arbitrary angle between the axis can be calculated.



Fig. 1. Coordinate system of the glass fabric reinforced plastic laminates.

ORIGINAL PAGE IS OF POOR QUALITY

2.2 Tension-compression combination biaxial failure criterion

The previous report (Reference (7)) studied the failure mode of the biaxial test results and the failure criterion was conducted from the results. In this report, the authors revised them and assumed that failure occurs under the following conditions.

(1) The condition in which σ_x or σ_y reaches uniaxial tensile strength $\sigma_{t(\theta)}$ or uniaxial compressive strength $\sigma_{c(\theta)}$ expressed in equation (2), i.e.

$$\sigma_{\mathbf{z}} = \sigma_t(\theta) \quad \text{or} \quad \sigma_{\mathbf{y}} = \sigma_t(\theta) \tag{3}$$

(2) The condition in which the shear stress τ_{LT} reaches the shear strength S_{LT} of the composite material. Since this study deals with tension-compression combination biaxial case, the relationships between σ_x and σ_y when failure occurs is as follows.

$$\sigma_x - \sigma_y = \frac{S_{LT}}{lm} \tag{4}$$

(3) By considering the influence of both perpendicular stress against the anisotropic axis L and T, and the shear stress, the combined stress which is from $\sigma_{e^{-v}}(\overline{\sigma^2 + r^2})$ (Reference (8)) was considered when σ_{e} reaches the uniaxial tensile strength $\sigma_i(\beta)$ or the uniaxial compression strength $\sigma_e(\beta)$ in the direction which corresponds to the direction of tan $\beta_{=\pi/\sigma}$, the following equations can be obtained where $\sigma_{e_{\ell}}$ and $\sigma_{e_{T}}$ is the combined stress against the other orientation axis L and T and their directions are $\beta_{\rm L}$ and $\beta_{\rm T}$ and $\sigma_{\rm x}/\sigma_{\rm y}$ is written as $-\phi$.

$$\sigma_{eL} = \sqrt{\sigma_L^2 + \tau_{LT}^2} = \sigma_x \sqrt{l^2 + \frac{m^2}{\varphi^2}}$$

$$\sigma_{eT} = \sqrt{\sigma_T^2 + \tau_{LT}^2} = \sigma_x \sqrt{m^2 + \frac{l^2}{\varphi^2}}$$

$$\beta_L = \tan^{-1} \frac{\tau_{LT}}{\sigma_L} = \tan^{-1} \frac{(\varphi + 1)lm}{\varphi l^2 - m^2}$$
(5)

$$\beta_r = \tan^{-1} \frac{\tau_{LT}}{\sigma_r} = \tan^{-1} \frac{(\varphi+1)lm}{\varphi m^2 - l^2}$$
(6)

From equation (2), (5) and (6)

$$\sigma_{z} = \frac{\sigma_{t}(\beta_{L})}{\sqrt{l^{2} + \frac{m^{2}}{\varphi^{2}}}} \quad \text{or} \quad \sigma_{z} = \frac{\sigma_{c}(\beta_{T})}{\sqrt{m^{2} + \frac{l^{2}}{\varphi^{2}}}}$$
(7)

 $\sigma_{\epsilon}(\beta_{L})$ and $\sigma_{\epsilon}(\beta_{T})$ are the values obtained by applying β_{L} and β_{T} of equation (9) to equation (5). The authors assumed that failure occurs at the minimum stress of equations (3), (4) and (7).

3. Test method

Three types of woven glass cloth were used. Fig.2 shows the weave of the glass cloth. (1) is a fabric with a little twisted wide roving cloth. (2) is a closely woven fabric with thin fiber. (3) is a fabric with the same thin fiber as (2) but is coarsely woven. In this report these fabrics (1), (2) and (3) are called

"Roving glass cloth", "Close plain woven glass cloth" and "Coarse plain woven glass cloth". The test specimens used non-saturated polyester as a matrix resin and were prepared by hand layup method. B.P.O 1.5 wt% was used as a hardener and the hardening condition was 90 °C for 4 hours. The specimens were laid up keeping 90 degrees of the ply orientation of each ply so that the strength of the laminates in the two directions is the same.



ORIGINAL PAGE IS OF POOR QUALITY



sion test specimen (b) Uniaxial compression test specimen Fig. 3. Dimensions of test specimen.

The dimensions of the specimens and the coordinates of the anisotropic axis are shown in Fig.3. (a) is the specimen for uniaxial tension test and combined biaxial test and (b) is the specimen for uniaxial compression. The dimensions of the specimen for the uniaxial test were determined as shown in Fig.3(b) after verifying that buckling failure does not occur in the preliminary tests.

The details of the tension-compression biaxial test equipment have been described in the previous report (Reference (7)).

/<u>18</u>

4. Test results and considerations

Fig.4 (a) to (c) and Fig.5(a) to (c) show the relationships between the orientation angle θ which is the angle between one anisotropic axis and the direction of applied tension or compression and failure stress. All of the test specimens were prepared to have equal strength in the elastic axis, thus the equation (2)' was applied. In the compression tests, the test results show large scatter thus 4 to 5 of the specimens were tested and the figure shows the maximum and the minimum stress.

The calculation and the test results seem to match well and in the case of compression, the failure stress of the specimens which have low fiber content and of the roving cloth is not influenced by the ply orientation angle θ and the failure stress was almost constant. Thus it was found that the equation (2)' matches the actual results well for uniaxial failure criterion. In general, the test methods for equation (2)' (or Equation(2)) have not been established and shear strength of which measurement stress is scattered is not included. Thus the equation is expressed only with tensile strength or compressive strength which are easy to obtain by test so it is practical.

From the equation (2) or (2)', physical meaning of failure can not be obtained. The failure mechanism of glass cloth laminates differs from tension or compression failure of uniaxial reinforced plastic. The failure criterion having physical meaning seems to be expressed with various unique factors of glass fiber fabric besides fiber content and layer strength such as tension, compression and shear in the fiber matrix. Therefore, it would be difficult to conduct such a criterion.

For tension-compression biaxial criterion, when the interaction formula, mentioned in the previous report (Reference (7)) using F_t for tensile strength, F_r for compressive strength and S_{LT} for shear strength was applied to the coarse plain woven glass cloth laminates, the result did not match the test results well. As can be found from equation (1), the uniaxial strength has discrepancy with a different value by considering the condition of uniaxial tension as a special case of combined biaxial tension or a special case of combination of tension and compression. But the interaction formula is a very simple formula so it is convenient in practical use.

ORIGINAL PAGE IS OF POOR QUALITY

ł



Here, the authors applied the interaction formula to the close plain woven glass cloth laminates and the roving glass woven laminates. Fig.6 (a) to (d) show comparison of the calculation results and test results. As shown in the figure, both match pretty well. Thus it seems to be able to be used as failure criterion for $\frac{19}{19}$ close plain woven glass cloth and roving glass cloth of which fibers are woven closely.

ORIGINAL PAGE IS



Fig. 5. The completion of unival failure criterion with the organization possils under unival compressive load.



interaction formula with the experimental results under biaxial loading.

The comparison of calculation results of equations (3), (4) and (7) which were conducted as new failure criteria and the test results is shown in Fig.7(a) to (c). In the case of the coarse plain woven glass cloth, the calculation results and the test results match well but in the case of the roving glass cloth and the close plain woven glass cloth which have wide weave or close weave the results did not match well. It may be from the interactive influence of the stress components σ_L and σ_r in the L and T direction in the case that $\theta = 0^\circ$. When compressive strength is low, this tendency occurred more. Compressive stress reduces in order with the coarse plain woven glass cloth, the close plain woven glass cloth and the roving glass cloth and this coincides with the order of weave roughness, and thickness of the fiber, i.e., the order of weave of the fiber which composes the fabrics. Thus it seems that the fabric with larger weave has larger mutual interference of σ_L and σ_r .

Equation (4) which expresses failure by shear stress in all of the cases coincided well with the test results. Under pure shear stress condition between the anisotropic axis (for example, the place where $\theta = 45^{\circ}$ and $\phi = -1$ in Fig.8(a)), shear failure occurs easily at 1/3 of tensile strength and about 1/2 of compressive strength in fiber direction for the roving glass cloth and the close plain woven glass cloth Therefore, it should be given enough attention.

The trend from equation (7) which expresses mutual interference of the perpendicular stress and the shear stress seems to match with the test results and in this case. also mutual influence of the components of the perpendicular stress in the L and T direction. /20



(a) Coarse plain woven class cloth. $V_f = 15\%$ (b) Close plain woven glass cloth. $V_f = 35\%$ (c) Formaz class cloth. $V_f = 35\%$

Fig. 7. The comparison of failure criterion, eqs. 6', '7', '5', with the experimental results under blacial loading.

5. Conclusions

Tension, compression and tension-compression biaxial tests were performed on three types of glass fiber fabric reinforced plastic laminates and the applicability of the generally used interaction formula was studied. Based on the results, new tension-compression combination biaxial failure criteria were conducted. The following conclusions were obtained.

(1) The interaction formula which is transformed into the formula for tensile or compressive strength instead of shear strength in the direction of 45° to one of the anisotropic axis can be used as an uniaxial failure criterion for glass cloth laminates.

(2) The interaction formula can be applied to closely woven plain fabric laminates as a tension-compression combination biaxial failure criterion but for coarsely woven plain fabric laminate, the formula does not agree with the test results.
(3) The authors studied the failure modes and a new tension-compression combination biaxial failure criterion was conducted. The tendency of calculation results and the test results coincided and when this criterion is applied to the case of uniaxial loading, the formula is the same as the formula used for tension or compression strength instead of shear strength in the direction of 45° to the anisotropic axis.

At last, the authors cordially thank Professor Hidekatsu Shiratori and Assistant Professor Kozo Ikegami of the Precision Engineering Institute of Tokyo Technical College for their assistance throughout this study. Lecture given at the 24th science council of the Japan Material Society on May 20, 1975)

References

- (1) Koichi Ohira : Kyudai Kogaku Shuho, 42,454 (1969)
- (2) Kozo Kawada : Zairyo, 20,881 (1971)
- (3) Puppo, A.H. and H.A. Evensen, AIAA Journal, 10, 468(1972)
- (4) Wu, E.M. and J.K.Scheublein, ASTM STP, 546, 188 (1974)
- (5) Sadao Amijima and Harunori Konami : Zairyo, 22, 1017 (1973)
- (6) Norris, C.B. : Forest Products Laboratory Report, 1816 (1962)
- (7) Osamu Haga, Noriyuki Hayashi and Kazuo Kasuya : Zairyo, 24, 776 (1975)
- (8) Hidekatsu Shiratori, Kozo Ikegami and Toshio Hattori : Zairyo, 22, 1802 (1973)

	ORIGINAL PAGE IS			
4. Title and Schulls 3. Presen Date FALLURE CRITERION OF GLASS FABRIC REINFORCED 3. Presen Date Archedi 5. Presen Date Osamu Haga, NOriyuki Hayashi and Kazuo Kasuya 1. Presen Date 9. Parlamang Organization Cale 1. Presen Date 9. Parlamang Organization Cale 1. Presen Date 9. Parlamang Organization Cale 1. Presen Date 9. Parlamang Organization Resent Address 10. Vert Unit No. 9. Parlamang Organization Resent Address 10. Vert Unit No. 9. Parlamang Organization Hense and Address 11. Contract or Grant No. 9. Statistics Address 11. Contract or Grant No. 9. Statistics Address 11. Translation Of "Class cloth sekiso kyoka plastic no hakai kijun", Japan Society of Materials Science, Journal, Vol. 25, No. 273, June 1976, pp. 516-520 (A76-41242). 4. Aburest Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, coarsely-woven plain fabric, and the organization formula is useful as the failure criterion in combined tensile compressive the anisotropic axes, for the unaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric 1 1. Data Addie Materie 1 1. Daterinteres	1. Report No. NASA TM- 88406	2. Government Acception No		J. Recipiont's Catalog No.
FAILURE CRITERION OF GLASS FABRIC REINFORCED APRIL 1986 PLASTIC LAMINATES APRIL 1986 7. Authoft) Osamu Haga, NOriyuki Hayashi and Kazuo Kasuya I. Futuring Organization Report No. 9. Performing Organization Name and Address II. Convert on Control No. II. Convert on Control No. 9. Performing Organization Name and Address II. Convert on Control No. II. Convert on Control No. 9. Performing Organization Name and Address II. Convert on Control No. II. Convert on Control No. 2. Statta Barbara, CA. 9110A II. Convert on Control Period Convert Translation 2. Suptimizer Netro II. Second Address II. Second Address 3. Second No. Control No. 20346 I. Second Address 4. Advicet Translation of "Class cloth sekiso kyoka plastic no hakai kijun", Japan Society of Materials Science, Journal, Vol. 25, No. 273, June 1976, pp. 516-520 (A76-41242). II. Second Period Per	4. Title and Subitile	- A		S. Report Data
PLASTIC LAMINATES 1. Festiming Organization Code 7. Awhed) Osamu Haga, NOriyuki Hayashi and Kazuo Kasuya 1. Festiming Organization Code 9. Pestiming Organization Mene and Address 10. Vest Unit Ne. 9. Pestiming Organization Mene and Address 11. Context or Graph Mene and Address SGUTRAN 10. Vest Unit Ne. 9. Statta Barbara, CA 9110B 11. Types of Research Mene and Address 2. Spatiation of "Class cloth sekiso kyoka plastic no hakai kijun", Japan Society of Materials Science, Journal, Vol. 25, No. 273, June 1976, pp. 516-520 (A76-41242). Abuvest Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one of the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates. 7. Key Toola (Stateste by Author(M) 10. Distributes Statesed 1 Unclassified 11. Proce Tables 1 11. Distributes Statesed 2 3. Stearty Cleastified and Doling tred 2 2. Stearty Cleasti	FAILURE CRITERION OF GLASS FABRIC REINFORCED PLASTIC LAMINATES			ADDIT 1004
7. Authods: I. Parlemang Organization Research the Osamu Haga, NOriyuki Hayashi and Kazuo Kasuya I. Parlemang Organization Research the 9. Perlemang Organization Neme and Address II. Type of Research to the Address SGUTRAN II. Convert at Guest Ne. Dox 5456 II. Type of Research Address Santa Barbara, CA. 9108 II. Type of Research Address * Struct Address Address Translation * Struct Address Address Translation * Struct Address Address June 1976, pp. 516-520 (A76-41242). * Advect Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, corsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is registed by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one or the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tensile claminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric 1 II. Dissibution Statement 1 Unclassified 1 Dissified and Staling of the speed 2 Steady Classi, fat data speerd 3				6. Performing Organization Code
Osamu Haga, NOriyuki Hayashi and Kazuo Kasuya In thinked Opennetics Report He Image: Second Secon	7. Author(s)			1 Pulu - D
9. Performing Organization Name and Address 9. Performing Organization Name and Address 9. Performing Organization Name and Address 9. SCITRAN Box 5456 Santa Barbara, CA. 9100A 11. Superior and Period Construction Vashington, D.C. 20546 12. Superior and Period Construction Vashington, D.C. 20546 13. Superior and Period Construction Vashington, D.C. 20546 14. Superior and Period Construction Vashington, D.C. 20546 15. Superior and Period Construction Vashington, D.C. 20546 16. Superior and Period Construction Vashington, D.C. 20546 17. Superior and Period Construction Vashington, D.C. 20546 18. Superior and Period Construction Vashington, D.C. 20546 19. Superior and Period Construction 10. Superior and Period Construction 11. Superior and Period Construction 12. Superior and Period Construction 13. Superior and Period Construction 14. Aborest	Osamu Haga, NOriyuki Ha	yashi and Kazuo Kasu	ya .	v. v everning Organisation Report No.
9. Performing Organization Near and Address 11. Contract or Grant Me. SCITRAN Box 5456 Santa Barbara, CA 9108 12. Type of Report and Period Contract 2. Symptom Ajercy Near and Address 14. Symmetry Ajercy Mean and Address Wational Aeronautice and Space Administration 14. Symmetry Ajercy Ajercy Mean and Address Wational Aeronautice and Space Administration 14. Symmetry Ajercy Ajercy Code 5. September Near Translation of "Glass cloth sekiso kyoka plastic no hakai kijun", Japan Society of Materials Science, Journal, Vol. 25, No. 273, June 1976, pp. 516–520 (A76–41242). A Abuted! Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one or the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tensile-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric 1 10. Distributen Statement 4 11. Contract of failure fabric 1 12. Security Closeli (af this paget) 1 13. Security Closeli (af this paget) <t< td=""><th></th><td></td><td></td><td>10. Work Unit No.</td></t<>				10. Work Unit No.
SCITRAN INSU- 4004 Box 5456 Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Translation Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, CA 910A Image: Santa Barbara, Data Santa Barbara, Ca 910A Image: Santa Barbara, Ca 910A Image: Santa Barbara, Data Santa	P. Performing Organization Name and Address		[11. Contract or Grant No.
Box 5656 Image: Santa Barbara, CA 9110A Image: Santa Barbara, CA 9110A Stanta Barbara, CA 9110A Translation Stanta Barbara, CA 9110A Image: Santa Barbara, CA 9110A Stanta Barbara, CA 9110A Image: Santa Barbara, CA 9110A Stanta Barbara, CA 9110A Image: Santa Barbara, CA 9110A Stanta Barbara, CA 9110A Image: Santa Barbara, CA 9110A Stanta Barbara, CA 9110A Image: Santa Barbara, CA 9110A Stanta Barbara, CA 9110A Image: Santa Barbara, CA 9110A Stanta Barbara, CA 9110A Image: Santa Barbara, CA 9110A Stanta Barbara, CA 9110A Image: Santa Barbara, CA 9110A Stanta Barbara, CA 9110A Image: Santa Barbara, CA 9110A Stanta Barbara, CA 9110A Image: Santa Barbara, CA 9110A Stanta Barbara, CA 910A Image: Santa Barbara, CA 910A Stanta Barbara, CA 910A Image: Santa Barbara, Ca 910A Stanta Barbara, CA 910A Image: Santa Barbara, Ca 910A Stanta Barbara, CA 910A Image: Santa Barbara, Ca 910A Translation of "Glass cloth sekiso kyoka plastic no bakai kijun", Japan Society of Materials Science, Journal, Vol. 25, No. 273, June 1976, pp. 516-520 (A76-41242). Aburst Failure criteria are derived for several modes of failure (in unaxial failur several motes cloth resile or comp	SCITRAN		. }	HASW- 4004
Santa Barbara, CA. 93108 Translation * Sympson Approx Marce and Space Administration It. Spanning Agency Code * Mational Aeronautics and Space Administration It. Spanning Agency Code * Massington, D.C. 20546 It. Spanner Agency Code * Support Agency Name It. Spanner Agency Code Translation of "Glass cloth sekiso kyoka plastic no hakai kijun", Japan Society of Materials Science, Journal, Vol. 25, No. 273, June 1976, pp. 516-520 (A76-41242). * Aburset" Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one co the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates. * Key Wede (Selected by Author(a) It. Orienterion Streame 1 Unclassified and Unlimited	Box 5456			13. Type of Report and Pariod Covered
************************************	<u>Santa Barbara, CA 9</u>	3108		Translation
Washington, D.C. 20546 14. Secondary Code S. Supplementery Netron Translation of "Glass cloth sekiso kyoka plastic no hakai kijun", Japan Society of Materials Science, Journal, Vol. 25, No. 273, June 1976, pp. 516–520 (A76–41242). A Absreet Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one or the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates. Y. Key Verde (Enterted by Author(14) 10. Distributen Sterement Inclassified 1 Inclassified and Palimited	National Aeronautics	and Space Adminiate		
S. Supplearning Networks Translation of "Glass cloth sekiso kyoka plastic no hakai kijun", Japan Society of Materials Science, Journal, Vol. 25, No. 273, June 1976, pp. 516–520 (A76–41242). A Abureat' Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one of the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates. 1. Contribute Strengt 1. Contribute Strengt 1. Description and Unitative during the sympt of the sympt of the sympt of the sympt of the sympt. The sympt of the sympt. The sympt of the sympt of the sympt of the sympt of the sympt. The sympt of the sympt of the sympt of the sympt. The sympt of the sympt. The sympt of the sympt of the sympt. The sympt of t	Washington, D.C. 201	546		14. Sponsoring Agoney Code
Translation of "Glass cloth sekiso kyoka plastic no hakai kijun", Japan Society of Materials Science, Journal, Vol. 25, No. 273, June 1976, pp. 516-520 (A76-41242). Abureat Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one of the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates. Key Vorde (Selected by Author(a) 10. Distributes Streams 1 Unclassified and Onlinited	5. Supplementary Natas			
Internation of "Glass cloth sekiso kyoka plastic no hakai kijun", Japan Society of Materials Science, Journal, Vol. 25, No. 273, June 1976, pp. 516-520 (A76-41242). Abured Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one of the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates. Key Veets (Selected by Author(1)) 10. Drivibution Statement 1 Unclassified and Unlimited				
June 1976, pp. 516-520 (A76-41242). Advanced Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one of the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates. Key Veeds (Selected by Author(M) 10. Draviturien Sterement 1 Unclassified 11. Pain	Lanan Society 5 M	cloth sekiso kyoka p	lastic	no hakai kijun".
Sume 1970, pp. 316-320 (A76-41242). Abside Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one or the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates. Key Words (Selected by Author(a) 10. Disributen Statement 1 Unclassified and Unlimited	Jupe 1976 pp 516 506	ials Science, Journa	1, Vol.	. 25, No. 273,
Abuvet Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one or the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates. Key Words (Interest by Author(14) 10. Distribution Statement I Unclassified	June 1970, pp. 516-520) (A/6-41242).		
Abstract ¹ Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one of the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates. Key Terds (Ediceted by Authoria) 10. Disribution Statement 1 Unclassified and Onlimited		_		
Abstract ¹ Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one of the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates. Y. Key Terds (Educted by Author(a)) 10. Drantbulken Stylement 1 Unclassified and Onlimited				
Failure criteria are derived for several modes of failure (in unaxial tensile or compressive loading, or biaxial combined tensile-compressive loading) in the case of closely woven plain fabric, coarsely-woven plain fabric, or roving glass cloth reinforcements. The shear strength in the interaction formula is replaced by an equation dealing with tensile or compressive strength in the direction making a 45 degree angle with one of the anisotropic axes, for the uniaxial failure criteria. The interaction formula is useful as the failure criterion in combined tension-compression biaxial failure for the case of closely woven plain fabric laminates, but poor agreement is ogtained in the case of coarsely woven fabric laminates. 2. Key Verds (Selected by Author(s) 10. Distribution Statement 1 Unclassified and Unlimited	L Abstract			
10. Distribution Statement 1 10. Distribution Statement 1	Failure criteria are d tensile or compressive loading) in the case o fabric, or roving glas interaction formula is compressive strength is the anisotropic axes, formula is useful as the biaxial failure for the but poor agreement is o laminates.	erived for several ma loading, or biaxial f closely woven plain s cloth reinforcement replaced by an equat n the direction makin for the uniaxial fail he failure criterion e case of closely wow ogtained in the case	odes of combin fabri s. Th ion de ag a 45 ure cr in com ren pla of coa	failure (in unaxial ed tensile-compressive c, coarsely-woven plain e shear strength in the aling with tensile or degree angle with one of iteria. The interaction bined tension-compression in fabric laminates, rsely woven fabric
. Security Classif. (of this report) 20. Security Classif. (of this page) 21. Me. of Pages 22. Price	. Koy Words (Selected by Authoria) 1	10, Diawib Unc	10. Distribution Statement Unclassified and Unlimited	
Unclassified Unclassified	. Security Classif. (of this report)	3. Security Claudi fad das		11. Ma _ 4 B
	Unclassified			4 ** *** ** * ** ** *** **************

. i | . |

. .