

Use Information: This paragraph is informational only and is not exclusively definitive of the end use.
For backing of pads and tablets and top and bottom protection in packaging.

Stock: *Not less than 80% postconsumer fiber. Any percent over 80 percentage points, is encouraged, provided that the requirements of this Standard are met.*

Thickness: Average (mils) 20.0
A tolerance of -0.001 inch and +0.002 inch shall be allowed.

Basis weight: 26 by 38 inches, 50 pounds
(number) sheets 100
A tolerance of $\pm 5\%$ shall be allowed.

Curl: Paperboard shall lie flat with either no tendency to curl or with a curl, which can be overcome, under reasonable working conditions.

Bursting strength: Average not less than
(lb/in²) 50

General appearance: The surface and cleanliness shall conform to the standard sample(s) established by the Government.

Testing: Shall be conducted in accordance with methods in part 2, *Government Paper Specification Standards*. The acceptance criteria Part 4 shall apply.