

**MICA (NATURAL), SCRAP AND FLAKE<sup>1</sup>**

(Data in thousand metric tons, unless otherwise noted)

**Domestic Production and Use:** Scrap and flake mica production, excluding low-quality sericite, was estimated to be 95,000 metric tons in 2001. North Carolina accounted for about 47% of U.S. production. The remaining output came from Georgia, New Mexico, South Carolina, and South Dakota. Scrap mica was recovered principally from mica and sericite schist and as a byproduct from feldspar, kaolin, and industrial sand beneficiation. The majority of domestic production was processed into small particle-size mica by either wet or dry grinding. Primary uses were joint compound, paint, roofing, oil well drilling additives, and rubber products. The value of 2001 scrap mica production was estimated at \$16.3 million. Ground mica sales in 2000 were valued at \$37.5 million. There were nine domestic producers of scrap and flake mica.

<b>Salient Statistics—United States:</b>	<b>1997</b>	<b>1998</b>	<b>1999</b>	<b>2000</b>	<b>2001<sup>e</sup></b>
Production: <sup>2 3</sup>					
Mine	112	87	95	101	95
Ground	110	104	111	112	106
Imports, mica powder and mica waste	23	23	21	29	32
Exports, mica powder and mica waste	8	8	11	10	10
Consumption, apparent <sup>4</sup>	122	137	125	119	118
Price, average, dollars per ton, reported:					
Scrap and flake	83	87	148	125	140
Ground:					
Wet	1,080	909	849	751	800
Dry	176	179	192	169	180
Stocks, producer, yearend <sup>e</sup>	NA	NA	NA	NA	NA
Employment, mine, number <sup>5</sup>	347	367	NA	NA	NA
Net import reliance <sup>6</sup> as a percentage of apparent consumption	10	13	10	15	19

**Recycling:** None.

**Import Sources (1997-2000):** Canada, 68%; India, 20%; Finland, 4%; China, 2%; and other, 6%.

<b>Tariff:</b>	<b>Item</b>	<b>Number</b>	<b>Normal Trade Relations</b>
			<b>12/31/01</b>
	Mica powder	2525.20.0000	Free.
	Mica waste	2525.30.0000	Free.

**Depletion Allowance:** 22% (Domestic), 14% (Foreign).

**Government Stockpile:** None.

## MICA (NATURAL), SCRAP AND FLAKE

**Events, Trends, and Issues:** Domestic production of ground mica decreased in 2001. The decrease primarily resulted from reduced production in Georgia, New Mexico, North Carolina, South Carolina, and South Dakota. Development continued at a recent mica operation in Arizona and the associated processing plant produced several wet ground mica products. The United States remained a major world producer of scrap and flake mica. Imported mica scrap and flake is primarily used for making mica paper and as a filler and reinforcer in plastics.

### World Mine Production, Reserves, and Reserve Base:

	Mine production		Reserves <sup>7</sup>	Reserve base <sup>7</sup>
	2000	2001 <sup>e</sup>		
United States <sup>2</sup>	101	95	Large	Large
Brazil	5	5	Large	Large
Canada	17	17	Large	Large
India	2	2	Large	Large
Korea, Republic of	30	30	Large	Large
Russia	100	100	Large	Large
Other countries	35	35	Large	Large
World total (may be rounded)	290	280	Large	Large

**World Resources:** Resources of scrap and flake mica are available in granite, pegmatite, schist, and clay deposits and are considered more than adequate to meet anticipated world demand in the foreseeable future.

**Substitutes:** Some of the lightweight aggregates, such as diatomite, vermiculite, and perlite, may be substituted for ground mica when used as a filler. Ground synthetic fluorophlogopite, a fluorine-rich mica, may replace natural ground mica for uses that require the thermal and electrical properties of mica.

<sup>e</sup>Estimated. NA Not available.

<sup>1</sup>See also Mica (Natural), Sheet.

<sup>2</sup>Sold or used by producing companies.

<sup>3</sup>Excludes low-quality sericite used primarily for brick manufacturing.

<sup>4</sup>Based on ground mica.

<sup>5</sup>Total employment at mines and mills where mica was produced and processed, excluding feldspar companies with byproduct production. Employees were not assigned to specific commodities in calculating employment.

<sup>6</sup>Defined as imports - exports + adjustments for Government and industry stock changes.

<sup>7</sup>See Appendix C for definitions.