

MICA (NATURAL), SCRAP AND FLAKE¹

(Data in thousand metric tons, unless noted)

Domestic Production and Use: Scrap and flake mica production, excluding low-quality sericite, decreased about 5% in 1995. North Carolina accounted for about 65% of U.S. production. The remaining output came from Georgia, New Mexico, South Carolina, and South Dakota. Scrap mica was recovered principally from mica and sericite schist and from feldspar, kaolin, and lithium beneficiation. The bulk of domestic production was processed into small particle-size mica by wet and dry grinding. Primary uses were joint compound, paint, roofing, oil well drilling additives, and rubber products. The value of 1995 scrap mica production was estimated at \$7.5 million. Ground mica sales were valued at \$29 million. There were 10 domestic producers of scrap and flake mica.

Salient Statistics—United States:	1991	1992	1993	1994	1995^e
Production: ^{2 3} Mine	103	85	88	109	104
Ground	75	84	92	95	91
Imports, mica powder and mica waste	11	12	14	18	16
Exports, mica powder and mica waste	4	4	5	6	7
Consumption, apparent ⁴	84	95	105	97	100
Price, average, dollars per ton, reported:					
Scrap and flake	54	51	51	66	65
Ground:					
Wet	640	745	838	1,007	1,000
Dry	150	168	152	151	150
Stocks, producer, yearend ^e	7	7	7	14	13
Employment, mine ^{e 5}	80	80	80	364	360
Net import reliance ⁶ as a percent of apparent consumption	11	12	12	1	10

Recycling: None.

Import Sources (1991-94): Canada, 90%; India, 6%; and other, 4%.

Tariff:	Item	Number	Most favored nation (MFN) 12/31/95	Non-MFN⁷ 12/31/95
	Mica powder	2525.20.0000	1.9% ad val.	20% ad val.
	Mica waste	2525.30.0000	Free	8.8¢/ kg.

Depletion Allowance: 22% (Domestic), 14% (Foreign).

Government Stockpile: None.

MICA (NATURAL), SCRAP AND FLAKE

Events, Trends, and Issues: Production of ground mica in the United States increased for the fourth consecutive year after 4 years of decline. The increase is a reflection of a continued improvement in construction activity. The United States remained the major producer of scrap and flake mica in 1995. Imported mica is used primarily for making mica paper and as a filler and reinforcer in plastics.

The principal environmental impact of mica mining was the land disturbance commonly associated with surface mining.

World Mine Production, Reserves, and Reserve Base:

	Mine production		Reserves ⁸	Reserve base ⁸
	1994	1995 ^e		
United States ²	109	104	Large	Large
Canada	18	18	Large	Large
India	2	2	Large	Large
Korea, South	8	8	Large	Large
Russia	25	25	Large	Large
Other countries	<u>52</u>	<u>52</u>	<u>Large</u>	<u>Large</u>
World total	214	209	Large	Large

World Resources: Resources of scrap and flake mica are available in granite, pegmatite, schist, and clay deposits and are considered more than adequate to meet anticipated world demand in the foreseeable future.

Substitutes: Some of the lightweight aggregates such as diatomite, vermiculite, and perlite may be substituted for ground mica when used as a filler. Ground synthetic fluorophlogopite, a fluorine-rich mica, may replace natural ground mica for uses that require the thermal and electrical properties of mica.

^eEstimated.

¹See also Mica (Natural), Sheet.

²Sold or used by producing companies.

³Excludes low-quality sericite used primarily for brick manufacturing.

⁴Based on ground mica.

⁵Total employment at mines and mills where mica was produced and processed, including byproduct production. Employees were not assigned to specific commodities in calculating employment.

⁶Defined as imports - exports + adjustments for Government and industry stock changes.

⁷See Appendix B.

⁸See Appendix C for definitions.