



# National Institute of Standards & Technology

## Certificate

### Standard Reference Material 388p

#### Isobutylene-Isoprene (Butyl) Rubber

This Standard Reference Material (SRM) is an isoprene-isobutylene copolymer rubber, IIR Type 218. SRM 388p is intended for use in checking the performance of Mooney Viscometers when used to characterize rubber and rubber like materials.

The SRM is in the form of a bale of the dried rubber weighing approximately 34 kg wrapped in polyethylene film and packaged in a cardboard carton. The SRM was baled from a single lot of the butyl rubber. One-kilogram samples were taken at the start and during the baling of every fifth bale of rubber for subsequent analysis to characterize the SRM. Two Mooney Viscosity measurements were made on each sample at both 100 °C and 125 °C according to the procedures described in ASTM Method D 1646-74. Both ML 1 + 4 and ML 1 + 8 values of the Mooney Viscosity Number were recorded at each temperature. The certified Mooney Viscosity Number values and associated uncertainties for the SRM are given below.

| <u>Temperature</u> | <u>Mooney Viscosity<br/>(ML 1 + 4)*</u> | <u>Mooney Viscosity<br/>(ML 1 + 8)**</u> | <u>Range of Measured<br/>Values</u> |
|--------------------|---|--|-------------------------------------|
| 100 °C             | 70.7 ± 1.3                              |  | 69.5 - 71.8                         |
| 100 °C             |   | 68.2 ± 1.2                               | 66.8 - 69.0                         |
| 125 °C             | 49.9 ± 1.2                              |  | 48.8 - 52.0                         |
| 125 °C             |   | 47.1 ± 0.85                              | 46.5 - 48.0                         |

\*ML 1 + 4 indicates that a large rotor was used; the sample was warmed in the viscometer for one minute before starting the motor; and the readings were taken 4 minutes after starting the motor.

\*\*ML 1 + 8 indicates that a large rotor was used; the sample was warmed in the viscometer for one minute before starting the motor; and the readings were taken 8 minutes after starting the motor.

NOTE: Each certified value represents the mean, plus or minus three standard deviations of 182 measurements at the indicated temperature (100 or 125 °) in the laboratories of the National Institute of Standards and Technology. User values different from the mean, but within the reported range of measured values, may be expected and should not be considered to represent a significant difference from the certified Mooney Viscosity Number.

CAUTION: This material should be stored in the dark and away from heat. Exposure to light and heat may affect the certified properties.

This lot of rubber was tested and certified in the Polymers Division, NIST Materials Science and Engineering Laboratory, by K.M Flynn and G.B. McKenna.

The technical and support aspects involved in the certification and issuance of this Standard Reference Material were coordinated through the Office of Standard Reference Materials by R.L. McKenzie.

Gaithersburg, MD 20899  
December 31, 1989

William P. Reed, Acting Chief  
Office of Standard Reference Materials