§ 177.1340 Ethylene-methyl acrylate copolymer resins.

Ethylene-methyl acrylate copolymer resins may be safely used as articles or components of articles intended for use in contact with food, in accordance with the following prescribed conditions:

- (a) For the purpose of this section, the ethylene-methyl acrylate copolymer resins consist of basic copolymers produced by the copolymerization of ethylene and methyl acrylate such that the copolymers contain no more than 25 weight percent of polymer units derived from methyl acrylate.
- (b) The finished food-contact article, when extracted with the solvent or solvents characterizing the type of food and under the conditions of time and temperature characterizing the conditions of its intended use as determined from tables 1 and 2 of §176.170(c) of this chapter, yields net chloroform-soluble extractives (corrected for zinc extractives as zinc oleate) in each extracting solvent not to exceed 0.5 milligram per square inch of food-contact surface when tested by the methods described in §176.170(d) of this chapter. If the finished food-contact article is itself the subject of a regulation in parts 174, 175, 176, 177, 178 and §179.45 of this chapter, it shall also comply with any specifications and limitations prescribed for it by that regulation.

NOTE: In testing the finished food-contact article, use a separate test sample for each required extracting solvent.

(c) The provisions of this section are not applicable to ethylene-methyl acrylate copolymer resins used in foodpackaging adhesives complying with § 175.105 of this chapter.

§ 177.1345 Ethylene/1,3-phenylene oxyethylene isophthalate/ terephthalate copolymer.

Ethylene/1,3-phenylene oxyethylene isophthalate/terephthalate copolymer (CAS Reg. No. 87365-98-8) identified in paragraph (a) of this section may be safely used, subject to the provisions of this section, as the non-food-contact layer of laminate structures subject to the provisions of §177.1395, and in blends with polyethylene terephthalate polymers complying with §177.1630.

- (a) Identity. For the purpose of this section, ethylene/1,3-phenylene oxyethylene isophthalate/terephthalate copolymer consists of the basic copolyproduced by the catalytic mer polycondensation of isophthalic acid and terephthalic acid with ethylene glycol and 1.3-bis(2hydroxyethoxy)benzene such that the finished resin contains between 42 and of mole-percent isophthalic moieties, between 2 and 8 mole-percent of terephthalic moieties, and not more than 10 mole-percent of 1,3-bis(2hydroxyethoxy)benzene moieties.
- (b) Specifications—(1) Density. Ethylene/1,3-phenylene oxyethylene isophthalate/terephthalate copolymer identified in paragraph (a) of this section has a density of 1.33±0.02 grams per cubic centimeter measured by ASTM Method D 1505-85 (Reapproved 1990), "Standard Test Method for Density of Plastics by the Density-Gradient Technique," which is incorporated by reference in accordance with 5 U.S.C. 552(a) and 1 CFR part 51. Copies may be obtained from the American Society for Testing and Materials, 1916 Race St., Philadelphia, PA 19103, or may be examined at the Center for Food Safety and Applied Nutrition's Library, Food and Drug Administration, 200 C St. SW., Washington, DC 20204, and the Office of the Federal Register, 800 North Capitol St. NW., suite 700, Washington, DC.
- (2) Softening point. Ethylene/1,3-phenylene oxyethylene isophthalate/ terephthalate copolymer identified in paragraph (a) of this section has a softening point of 63±5 °C as measured by ASTM Method D 1525-87, "Standard Test Method for VICAT Softening Temperature of Plastics," which is incorporated by reference in accordance with 5 U.S.C. 552(a) and 1 CFR part 51. The availability of this material is provided in paragraph (b)(1) of this section.
- (c) Optional adjuvant substances. Ethylene/1,3-phenylene oxyethylene isophthalate/terephthalate copolymer, identified in paragraph (a) of this section, may contain optional adjuvant substances required in their production. The optional adjuvants may include substances used in accordance with §174.5 of this chapter.