

Use information: This paragraph is informational only and is not exclusively definitive of the end use.

For face and back multicolor offset printing of books, pamphlets, catalogs, folders, circulars, etc.; light colors suitable for printing solid reverses or heavy halftones. Printed matter may include text, line illustrations, and halftones up to 150-line screen. Sheets 216 by 356 mm (8½ by 14 inches) or smaller are used principally for reproduction by small offset presses at speeds in excess of 2,000 copies per hour.

Stock: Groundwood pulp, not to exceed 1 pct.

Note: Not less than 30 pct postconsumer fiber. Any percent over 30 percentage points, is encouraged, provided that the requirements of this Standard are met.

Grammage (g/m ²)	75	90	105
Basis weight: 25 by 38 inches, 500 sheets (pounds)	50	60	70

A tolerance of ±5 pct shall be allowed.

Bursting strength: Average, not less than (kPa)	110	130	150
Equivalent (lb/in ²)	16	19	22

Opacity: Average, not less than (percent)	90	92	93
No individual specimen shall average less than (percent)	88	90	91

Thickness: Average (mm)	0.100	0.120	0.140
Equivalent (inch)	0.0039	0.0047	0.0055

A tolerance of ±0.013 mm (0.0005 inch) shall be allowed. Paper shall be uniform and shall not vary more than 0.011 mm (0.0004 inch) from one edge to the other.

General appearance: Paper shall conform to the standard sample(s) adopted by the Government.

Color: The paper in the order (or publication) shall be uniform. The color variation shall not exceed DE(CIELAB)=1.0.

For colored stock, paper shall match one of the established standards or as specified. Colors shall not fade or transfer (rub off) and shall appear even and uniform on the surface of the sheet. Stock shall not be 2-sided. Color coordinates for selected standards are included in Part 3.

Finish and formation: Shall be uniform.

Cleanliness: The dirt count for each side of the paper shall not exceed 650 specks per square meter. No sample sheet (600 to 650 cm² in size) shall contain more than one defect with an equivalent area of 0.25 mm² or greater.

Note: This property is automatically waived when the ordering agency has specified a stock which includes "fibers" or "specks" in the surface of the sheet.

Sampling and testing: Shall be conducted in accordance with standards in Part 2, *Government Paper Specification Standards*.

Unless otherwise specified, the following is automatically waived when printing or duplicating is to be accomplished on commercial contract

Sizing: Paper shall be surface- and internal-sized suitable for satisfactory printing on both sides of the paper on high-speed offset presses and/or sheet-fed offset presses equipped with continuous flow or brush dampening systems.

Tensile strength: For roll stock only, average, not less than—			
Machine direction (kN/m)	3.5	3.8	4.1
Cross direction (kN/m)	1.4	1.6	1.8
Equivalent—			
Machine direction (kg/in)	9.0	9.7	10.5
Cross direction (kg/in)	3.6	4.1	4.6

Pick resistance: Sheet-fed offset: Average, each side, not less than 13-A Dennison wax number for sheet size exceeding 432 by 559 mm (17 by 22 inches); 10-A Dennison wax number for sheet sizes 432 by 559 mm (17 by 22 inches) or less.

Web offset: Average, each side, not less than 11-A Dennison wax number.

No individual specimen shall average less than 11-A, 8-A, and 9-A Dennison wax number, respectively.

Color: Shall match the Government's standard sample for color. A deviation of DE(CIELAB)=2.0 from the color standard is allowed. A color difference 1.0 DE unit between the wire and felt sides is permitted.

Curl: Paper shall lie flat with either no tendency to curl or with a curl which can be overcome under reasonable working conditions.

Surface: Shall be free from lint, fuzz, or any particles which will pick, lift, fluff, or pile on the blanket under normal press conditions.

Size and trim: Sheets: Paper shall be furnished in the size(s) ordered and shall be flat, trimmed square on four sides with clean

smooth edges, and evenly jogged. A tolerance of ±2 mm (¼ inch) shall be allowed except for sheets 216 by 356 mm (8½ by 14 inches) or less; then a tolerance of ±1 mm (⅜ inch) shall be allowed. Successive sheets within any package shall not differ from each other by more than 0.5 mm (⅛ inch). Paper with the long dimension 813 mm (32 inches) or less shall be considered square if the variation does not exceed 1 mm (⅜ inch); over 813 mm (32 inches); 2 mm (¼ inch).

Rolls: Roll width and diameter shall be as ordered. A tolerance of ±2 mm (¼ inch) shall be allowed for width and ±26 mm (1 inch) for diameter.

Roll winding: Roll paper shall be tightly wound at even tension and shall not contain more than the specified maximum number of splices per roll. The number of splices permitted per roll is determined by the roll diameter as ordered. On rolls 1,016 mm (40 inches) or less, a maximum of three splices per roll shall be allowed. On rolls over 1,016 mm (40 inches), a maximum of four splices per roll shall be allowed. Splices shall be neatly and securely overlap-pasted and made with a repulpable adhesive which will not permit the splice to separate. The adhesive may be applied from a tape form backing, provided the backing is removed, leaving only the adhesive component on the splice. The adhesive shall not cause the splice to adhere to adjacent laps. The tails of the splices shall be neatly and evenly removed without damage to adjacent laps. Splices shall be flagged at both ends with projecting colored markers, not pasted to the splice, or otherwise clearly marked.

Grain: Direction of the grain on flat paper shall be as ordered.

Pressroom conditions: The bulk of this paper will be used in air-conditioned pressrooms maintained at 24°C ±2°C and 45 pct ±8 pct relative humidity.