



# NEPCOAT Qualified Products List A

for Protective Coatings for  
NEW and 100% BARE EXISTING Steel for Bridges

NTPEP System No.	Coats	3-COAT SYSTEM TESTED AND ACCEPTED	Slip Coef	Manuf'r Class	VOC mil	QPL Accepted Dates
------------------	-------	-----------------------------------	-----------	---------------	---------	--------------------

**NEPCOAT LIST A - INORGANIC Zinc Rich Primer / Epoxy or Urethane Intermediate / Aliphatic Urethane Finish**

SSC(03)-01 (A7-97)	CARBOLINE COMPANY					from	
	Primer	Carbozinc® 11 HS Inorganic Zinc Primer	B <sup>1</sup>	2-6	50-150	278	2/15/05
	Interm	Carboguard® 893 Epoxy Intermediate		3-6	75-150	189	until
	Topcoat	Carbothane 133 HB Aliphatic Polyurethane		3-7	75-175	370	spring 2010
	<sup>1</sup> Footnote	6 mils max DFT, 18 hrs min cure, 15 oz/gal max thin					
SSC(04)-04*	ICI PAINTS / DEVOE COATINGS					from	
	Primer	Catha-Coat® 304V Silicate Inorganic Zinc Coating	B <sup>1</sup>	2-4	50-100	319	10/5/06
	Interm	Bar-Rust® 231 Multi-Purpose Epoxy Mastic		4-8	100-200	229	until
	Topcoat	Devthane® 379UVA Aliphatic Urethane Enamel		2-3	50-75	255	fall 2010
	<sup>1</sup> Footnote	3 mils max DFT, 24 hrs min cure, zero max thin'r					
SSC(06)-05*	CARBOLINE COMPANY					from	
	Primer	Carbozinc® 11 HS Inorganic Zinc Primer	B <sup>1</sup>	2-6	50-150	323	06/21/07
	Interm	Carboguard® 893 Epoxy Intermediate		3-6	75-150	200	until
	Topcoat	Carbothane 133 LH Aliphatic Polyurethane		3-6	75-150	295	spring 2011
	<sup>1</sup> Footnote	6 mils max DFT, 18 hrs min cure, 15 oz/gal max thin					

<sup>1</sup> Footnote Information from the Slip-Coefficient and Creep Resistance Test Certificate is given for use w/ primed bolted connections.

NOTE 1 NEPCOAT- NORTHEAST PROTECTIVE COATINGS COMMITTEE of CT, DE, ME, MA, NH, NJ, NY, PA, RI, VT

2 NTPEP (Nat'l Transport'n Product Evaluat'n Program). See Structural Steel Coating test data at <http://data.ntpep.org>.

3 Accelerated lab and field testing of coating systems is performed according to AASHTO NTPEP R-31 criteria.

4 Systems are accepted for use on NEW and 100% BARE EXISTING steel for bridges cleaned by abrasive blasting.

5 SSC(yr)-xx systems comply with AASHTO R-31 Evaluation Practice & NEPCOAT Acceptance Criteria.

6 VOC values are lab test results using unthinned samples. NEPCOAT max VOC limit is 420 g/L (3.5 lb/gal). Individual state requirements for VOC limits may differ.

7 Recommended DFT values are listed by manufacturer (see NTPEP DataMine Test 7). Also check Product Data Sheets.

8 Any change in coating formulation from that tested will result in removal of the system from the QPL.

9 The QPL term is 5 years starting from the date of acceptance until the next biannual NEPCOAT meeting. See R-31.

\* Acceptance is CONDITIONAL pending submission within four years of successful 2-year field history. A startup list of five bridges painted with the paint system must be submitted within two years. See Acceptance Criteria.

\*\* Requalification is per R-31, sect. 12.1, except that the manufacturer has an additional (6th) year to complete the 5-year requalification term if the identical system is being retested at the end of the 5-year term.



# NEPCOAT Qualified Products List B

for Protective Coatings for  
NEW and 100% BARE EXISTING Steel for Bridges

NTPEP System No.	Coats	3-COAT SYSTEM TESTED AND ACCEPTED	Slip Coef	Manuf'r Class	Coating mil	VOC micron	QPL g/L Dates
<b>NEPCOAT LIST B - ORGANIC Zinc Rich Primer / Epoxy or Urethane Intermediate / Aliphatic Urethane Finish</b>							
SSC(03)-02 (B7-97)		CARBOLINE COMPANY					from
	Primer	Carbozinc® 859 Organic Zinc Rich Epoxy Primer	B <sup>1</sup>	3-10	75-225	326	2/15/05
	Interm	Carboguard® 888 Epoxy Polyamide		3-10	75-225	331	until
	Topcoat	Carbothane 133 HB Aliphatic Polyurethane		3-7	75-175	370	spring 2010
	<sup>1</sup> Footnote	6 mils max DFT, 4 days min cure, 10% vol max thin					
SSC(03)-05*		AMERON INTERNATIONAL					from
	Primer	Amercoat® 68HS Zinc Rich Epoxy Primer	A <sup>1</sup>	1-3	25-75	240	11/17/05
	Interm	Amercoat® 399 Fast Drying Epoxy		4-8	100-200	182	until mtg.
	Topcoat	Amercoat® 450H Gloss Aliphatic Polyurethane		2-3	50-75	303	fall 2009
	<sup>1</sup> Footnote	Slip coefficient does not meet Class B requirements					
SSC(03)-12*		INTERNATIONAL PAINT INC					from
	Primer	Interzinc® 52 Epoxy Zinc Rich	Ø	2-3	50-75	364	2/15/05
	Interm	Intergard 475HS Epoxy	(not tested)	4-8	100-200	191	until
	Topcoat	Interfine® 979 Polysiloxane		3-6	75-150	206	fall 2009
	Ø Footnote	The test was not performed.					
SSC(04)-02*		CARBOLINE COMPANY					from
	Primer	Carbozinc® 859 Organic Zinc Rich Epoxy Primer	B <sup>1</sup>	3-10	75-250	327	11/17/05
	Interm	Carboguard® 888 Epoxy Polyamide		3-8	75-200	320	until mtg.
	Topcoat	Carbothane 133 LH Aliphatic Polyurethane		3-6	75-150	311	fall 2009
	<sup>1</sup> Footnote	6 mils max DFT, 4 days min cure, 10% vol max thin					
(continues)		(List B continues)					(List B continues)
<sup>1</sup> Footnote	Information from the Slip-Coefficient and Creep Resistance Test Certificate is given for use w/ primed bolted connections.						
NOTE 1	NEPCOAT- NORTHEAST PROTECTIVE COATINGS COMMITTEE of CT, DE, ME, MA, NH, NJ, NY, PA, RI, VT						
2	NTPEP (Nat'l Transport'n Product Evaluat'n Program). See Structural Steel Coating test data at <a href="http://data.ntpep.org">http://data.ntpep.org</a> .						
3	Accelerated lab and field testing of coating systems is performed according to AASHTO NTPEP R-31 criteria.						
4	Systems are accepted for use on NEW and 100% BARE EXISTING steel for bridges cleaned by abrasive blasting.						
5	SSC(yr)-xx systems comply with AASHTO R-31 Evaluation Practice & NEPCOAT Acceptance Criteria.						
6	VOC values are lab test results using unthinned samples. NEPCOAT max VOC limit is 420 g/L (3.5 lb/gal). Individual state requirements for VOC limits may differ.						
7	Recommended DFT values are listed by manufacturer (see NTPEP DataMine Test 7). Also check Product Data Sheets.						
8	Any change in coating formulation from that tested will result in removal of the system from the QPL.						
9	The QPL term is 5 years starting from the date of acceptance until the next biannual NEPCOAT meeting. See R-31.						
*	Acceptance is CONDITIONAL pending submission within four years of successful 2-year field history. A startup list of five bridges painted with the paint system must be submitted within two years. See Acceptance Criteria.						
**	Requalification is per R-31, sect. 12.1, except that the manufacturer has an additional (6th) year to complete the 5-year requalification term if the identical system is being retested at the end of the 5-year term.						



# **NEPCOAT Qualified Products List B**

for Protective Coatings for  
**NEW and 100% BARE EXISTING Steel for Bridges**

NTPEP System No.	Coats	<b>3-COAT SYSTEM</b> TESTED AND ACCEPTED	Slip Coef	Manuf'r Coating Class	VOC mil	QPL Accepted Dates
			DFT (min/max)	micron	g/L	
<b>NEPCOAT LIST B - ORGANIC Zinc Rich Primer / Epoxy or Urethane Intermediate / Aliphatic Urethane Finish</b>						
SSC(04)-03		SHERWIN WILLIAMS COMPANY				from
Primer	Zinc Clad® III HS Organic Zinc Rich Epoxy Primer	B <sup>1</sup>	3-5	75-125	330	11/17/05
Interm	Macropoxy® 646 Fast Cure Epoxy		5-10	125-250	191	until mtg.
Topcoat	Acrolon™ 218 HS Acrylic Polyurethane		3-6	75-150	280	fall 2010
<sup>1</sup> Footnote	5 mils max DFT, 7 days min cure, zero thinner					
SSC(05)-02*		MAB PAINTS				from
Primer	Ply-Tile Epoxy Organic Zinc Rich Primer	---	<sup>1</sup> 3-5	75-125	404	10/5/06
Interm	Ply-Mastic 650 HB Epoxy Coating		4-6	100-150	270	until
Topcoat	Ply-Thane 890 HS Aliphatic Acrylic Urethane		2-4	50-100	256	fall 2010
<sup>1</sup> Footnote	Slip coefficient is under retest					
SSC(06)-11*		CARBOLINE COMPANY				from
Primer	Carbozinc® 859 Organic Zinc Rich Epoxy Primer	B <sup>1</sup>	3-10	75-250	327	4/7/09
Interm	Carboguard® 893 Epoxy Polyamide		3-10	75-250	200	until mtg.
Topcoat	Carbothane 133 LH Aliphatic Polyurethane		3-6	75-150	311	spring 2013
<sup>1</sup> Footnote	6 mils max DFT, 4 days min cure, 10% vol max thin					
SSC(07)-02*		INTERNATIONAL PAINT INC				from
Primer	Interzinc® 315B Epoxy Zinc Rich	Ø	2-6	50-150	291	4/7/09
Interm	Intergard 475HS Epoxy	(not tested)	4-8	100-200	177	until mtg.
Topcoat	Interthane® 870 UHS		3-5	75-125	171	spring 2013
$\emptyset$ Footnote	The test was not performed.					
<sup>1</sup> Footnote	Information from the Slip-Coefficient and Creep Resistance Test Certificate is given for use w/ primed bolted connections.					
NOTE 1	NEPCOAT- NORTHEAST PROTECTIVE COATINGS COMMITTEE of CT, DE, ME, MA, NH, NJ, NY, PA, RI, VT					
2	NTPEP (Nat'l Transport'n Product Evaluat'n Program). See Structural Steel Coating test data at <a href="http://data.ntpep.org">http://data.ntpep.org</a> .					
3	Accelerated lab and field testing of coating systems is performed according to AASHTO NTPEP R-31 criteria.					
4	Systems are accepted for use on NEW and 100% BARE EXISTING steel for bridges cleaned by abrasive blasting.					
5	SSC(yr)-xx systems comply with AASHTO R-31 Evaluation Practice & NEPCOAT Acceptance Criteria.					
6	VOC values are lab test results using unthinned samples. NEPCOAT max VOC limit is 420 g/L (3.5 lb/gal). Individual state requirements for VOC limits may differ.					
7	Recommended DFT values are listed by manufacturer (see NTPEP DataMine Test 7). Also check Product Data Sheets.					
8	Any change in coating formulation from that tested will result in removal of the system from the QPL.					
9	The QPL term is 5 years starting from the date of acceptance until the next biannual NEPCOAT meeting. See R-31.					
*	Acceptance is CONDITIONAL pending submission within four years of successful 2-year field history. A startup list of five bridges painted with the paint system must be submitted within two years. See Acceptance Criteria.					
**	Requalification is per R-31, sect. 12.1, except that the manufacturer has an additional (6th) year to complete the 5-year requalification term if the identical system is being retested at the end of the 5-year term.					



# NEPCOAT Qualified Products List C

for Protective Coatings for  
NEW and 100% BARE EXISTING Steel for Bridges

NTPEP System No.	Coats	2-COAT SYSTEM <sup>10</sup> TESTED AND ACCEPTED	Slip Coef	Manuf'r Coating Class	VOC mil	QPL Accepted Dates
------------------	-------	--	-----------	-----------------------	---------	--------------------

NEPCOAT LIST **C** - ORGANIC Zinc Rich Primer / ----- / Topcoat

SSC(02)-04	SHERWIN WILLIAMS COMPANY					from
Primer	Corothane® I Galvapac One Pack Zinc Primer	B <sup>1</sup>	3.5-4	90-100	298	4/19/05
Interim	-----		---	---	---	until
Topcoat	Fast Clad® Urethane		6-9	150-225	263	spring 2010

<sup>1</sup> Footnote 4 mils max DFT, 24 hrs min cure

- <sup>1</sup> Footnote Information from the Slip-Coefficient and Creep Resistance Test Certificate is given for use w/ primed bolted connections.
- NOTE 1 NEPCOAT- NORTHEAST PROTECTIVE COATINGS COMMITTEE of CT, DE, ME, MA, NH, NJ, NY, PA, RI, VT
- 2 NTPEP (Nat'l Transport'n Product Evaluat'n Program). See Structural Steel Coating test data at <http://data.ntpep.org>.
- 3 Accelerated lab and field testing of coating systems is performed according to AASHTO NTPEP R-31 criteria.
- 4 Systems are accepted for use on NEW and 100% BARE EXISTING steel for bridges cleaned by abrasive blasting.
- 5 SSC(yr)-xx systems comply with AASHTO R-31 Evaluation Practice & NEPCOAT Acceptance Criteria.
- 6 VOC values are lab test results using unthinned samples. NEPCOAT max VOC limit is 420 g/L (3.5 lb/gal). Individual state requirements for VOC limits may differ.
- 7 Recommended DFT values are listed by manufacturer (see NTPEP DataMine Test 7). Also check Product Data Sheets.
- 8 Any change in coating formulation from that tested will result in removal of the system from the QPL.
- 9 The QPL term is 5 years starting from the date of acceptance until the next biannual NEPCOAT meeting. See R-31.
- \* Acceptance is CONDITIONAL pending submission within four years of successful 2-year field history. A startup list of five bridges painted with the paint system must be submitted within two years. See Acceptance Criteria.
- \*\* Requalification is per R-31, sect. 12.1, except that the manufacturer has an additional (6th) year to complete the 5-year requalification term if the identical system is being retested at the end of the 5-year term.



# **NEPCOAT Acceptance Criteria List A, B, C**

for Protective Coatings for  
**NEW and 100% BARE EXISTING Steel for Bridges**

AASHTO R31-Testing Standard & NEPCOAT Acceptance Criteria (3/16/04, 2/15/05, 10/16/08, 4/7/09)

## **TEST NO. 1 - SLIP COEFFICIENT**

<u>Primer</u>	Acceptance criteria (min.)
IOZ	Slip coefficient 0.5 (Class B) required
OZ	Report results only

## **TEST NO. 2 - SALT FOG RESISTANCE (ASTM B117)**

Delamination	Acceptance criteria: no delamination allowed
Rust / Blistering	Acceptance criteria (max.):

<u>Primer</u>	<u>System</u>	RUST CRITERIA					-- BLISTER CRITERIA--	
		@ Hrs	max creep	ave creep	% length	in scribe	@ Hrs	Convers'n #
IOZ	P-I-T	5000	4 mm	2 mm	not req'd	not req'd	4000	8
OZ	P-I-T	5000	8 mm	2 mm	not req'd	not req'd	4000	7

## **TEST NO. 3 - CYCLIC WEATHERING RESISTANCE (ASTM D5894)**

Delamination	Acceptance criteria: no delamination allowed
Rust / Blistering	Acceptance criteria (max.):

<u>Primer</u>	<u>System</u>	RUST CRITERIA					-- BLISTER CRITERIA--	
		@ Hrs	max creep	ave creep	% length	in scribe	@ Hrs	Convers'n #
IOZ	P-I-T	5040	4 mm	2 mm	not req'd	not req'd	4032	9
OZ	P-I-T	5040	8 mm	4 mm	not req'd	not req'd	4032	8

GLOSS value	Acceptance criteria: Report results only
GLOSS % Retent'n	Acceptance criteria: Report results only
COLOR Change, $\Delta e$	Acceptance criteria: Report results only

## **TEST NO. 4 - ABRASION RESISTANCE (ASTM D4060)**

Weight Loss	Acceptance criteria: Report results only
Wear Index	Acceptance criteria: Report results only

## **TEST NO. 5 - ADHESION (ASTM D4541)**

Pull-Off Strength	Acceptance criteria (min.) for both primer and PIT panels:
IOZ	2.4 MPa (350 psi)
OZ	4.1 MPa (600 psi)

## **TEST NO. 6 - FREEZE THAW STABILITY**

Pull-Off Strength	Acceptance criteria: achieve min. Test 5 req'd PIT adhesion results and fall within 60% of Test 5 values
-------------------	--

## **TEST NO. 7 - COATING IDENTIFICATION TESTS**

VOC	Acceptance criteria: Max. 420 g/L (3.5 lb/gal). Individual state requirements may differ.
Coating properties	Acceptance criteria: Report only
Coating thickness	Acceptance criteria: A 2-coat system shall be tested and applied at min. total 9 mils DFT.

(continued)



# NEPCOAT Acceptance Criteria List A, B, C

## for Protective Coatings for NEW and 100% BARE EXISTING Steel for Bridges

AASHTO R31-Testing Standard & NEPCOAT Acceptance Criteria (3/16/04, 2/15/05, 10/16/08, 4/7/09)

### TEST NO. 8 - ATMOSPHERIC EXPOSURE (TWO YEAR) at ocean beach site

Acceptance criteria: To be determined / Report results

### ITEM NO. 9 - FIELD HISTORY (TWO YEAR)

Acceptance criteria: (All systems after SSC 06-05) The coating manufacturer must submit two notifications;

- (1) a startup list within two years of product acceptance identifying five bridges (in a cold/wet climatic region) which have been coated with a minimum of 400 liters (100 gallons) of the coating system (i.e. total volume of primer, intermediate and topcoat); and
- (2) the same list of bridges within four years of product acceptance after the system has two years (min.) of successful field performance. "Successful performance" is simply defined as whether the Owner is satisfied with its application and performance to date, and whether the Owner would recommend the use of the coating again.

### PRODUCT VERIFICATION TESTING

AASHTO R-31 Appendix recommends that the Owner perform product verification testing for determining if the coatings supplied to a project are the same quality as the manufacturer's materials originally tested and certified for acceptance.

The R-31 Test 7- Coating Identification Tests are described in Sect. 9 and Appendix X1, and the lab test results are given in NTPEP DataMine (<http://data.ntpep.org>) along with the manufacturer's listed values.

When the Owner performs verification testing, the following tolerances apply:

<u>Verification Test</u>	<u>R-31 Section</u>	<u>R-31 App X1</u>	<u>ASTM Test</u>	<u>DataMine Test 7</u>	<u>Tolerance *</u>
Total solids (% by mass)	9.7.13.1	X1.1.1.1.6	D 2369	Line 2	$\pm 5\%$
Pigment (% by mass)	9.7.13.5	" 8	D 2371	" 3	$\pm 5\%$
Mass per volume (g/L)	9.7.13.8	" 5	D 1475	" 6	$\pm 2\%$
Viscosity (Stormer)	9.7.13.9	" 4	D 562	" 7	$\pm 8\%$

\* The tolerance is applied to the DATAMINE "test result" value (not the manufacturer's "listed value").

These tolerances apply to the primer and intermediate coats each in their mixed condition (not Part A, Part B components). For topcoats, if the color is different from the original color in NTPEP testing, then these tolerances apply to the Owner's verification test values the first time a particular color is used.