

Nuclear Density Gauge Readings on First Lift of P-154

Station	Offsets	Dry Density, pcf	MC, %	% Compaction
880	4N	127.9	4.9	95.6
	CL	128.2	5.0	95.8
	4S	127.5	5.3	95.3
900	4N	132.2	4.9	98.8
	CL	130.2	5.3	97.3
	4S	127.1	5.1	95.0
920	4N	133.1	5.1	99.5
	CL	129.9	4.8	97.1
	4S	129.1	4.5	96.5
890	CL	134.5	4.2	100.5
910	CL	130.7	4.7	97.7
925	CL	128	5.0	95.7

Nuclear Density Gauge Readings on Second Lift of P-154

Station	Offsets	Dry Density, pcf	MC, %	% Compaction
885	4N	131.3	4.8	98.1
	CL	129.5	4.9	96.8
	4S	131.5	4.9	98.3
900	4N	130.4	5	97.5
	CL	128	5.1	95.7
	4S	131.9	5	98.6
915	4N	131.8	4.9	98.5
	CL	132.2	5.1	98.8
	4S	133.5	4.9	99.8
885	6S	133.5	4.9	99.8
900	2S	133.8	5.1	100.0
900	CL	132.6	5.2	99.1
910	CL	132.7	4.9	99.2
915	2N	135.2	4.8	101.0